



## BaseLine

# Silk Matt Varnish SM 211-40

### Specification

- Dispersion varnish, silk matt
- Good silk matte result
- Good drying
- Good slip value
- Good polishing
- Anilox recommendation 10ccm - 13ccm anilox hexagonal
- Good rub resistance
- Very good block resistance
- Double side application
- Good hot foil stamping application (application-related work sample required)
- Good film lamination and UV varnishing (application-related work sample required)
- Glue application could be possible (application-related work sample required)
- Can be used on all delivery
- Can be used on paper and cardboard
- Production viscosity 38 sec. – 50 sec

Different viscosity settings are possible on request.

### Food print:

Can be used for indirect food contact.

For safe food print, please use the certified dispersion coatings from our Varcotec FoodLine series.

### Drying:

With IR and warm air.

### Viscosity:

Measured at 20 °C and with a DIN 4 mm cup.

Please dilute higher viscosity with water to the production viscosity.

### Application:

On all commercial varnish unit of the sheet fed print machines, separate varnish unit and coating machine.

### Notes:

Stir packages well before use.

The specifications depend on the substrate and varnish application volume.

Only use printing inks that are solvent-proof, alkali-proof and spirit-proof according to ISO 2836.

Clean with water.

For reasons of safety, we recommend leaving out the glue tabs.

### Storage:

Store the closed packages at 5 °C – 35 °C.

Protect from direct sunlight, heat and frost.

This Varnish has a 5 years shelf life - if unopened and stored in the correct conditions.